



ARCTIC PAPER

MUNKEN KRAFT HIGHWHITE from Arctic Paper Kostrzyn

Munken Kraft HighWhite is a machine finished Bleached Kraft paper with high whiteness, suitable for polymer-coating, various bag, wrapping and packaging applications. The paper is produced with a mixture of softwood and hardwood virgin fibre to give it high strength and good printability.

Munken Kraft HighWhite is available as FSC® – The mark of responsible forestry. www.fsc.org. FSC® C012880 and PEFC™ PEFC/01-31-126 certified and holds an ISEGA certificate of compliance for food contact.



BASIC INFORMATION

Grammages from 38 to 60 g/m²

CERTIFICATES / STATEMENTS

FSC, PEFC, ISO 14001, EMAS, Paper Profile, ISEGA certificate (food contact)

PRINTING TECHNIQUES

Flexo, Offset

SHADE

Highwhite

SURFACE

Machine Finished

MUNKEN KRAFT HIGHWHITE

Grammage (g/m ²)	38	40	45	50	55	60
Thickness (µm)	51	54	59	65	72	78
Bulk (cm ³ /g)	1.35	1.35	1.3	1.3	1.3	1.3
Roughness (Bendtsen, ml/min)	200	200	200	200	200	200
Opacity (%)	53	55	59	64	66	68
Brightness (ISO 2470/D65, %)	101	101	101	101	101	101
Whiteness (CIE)	141	141	141	141	141	141
Cobb ₆₀ (g/m ²)	25	25	25	25	25	25
Moisture (%)	6	6	6	6	6	6
Tensile Strength MD (ISO 1924-2, kN/m)	3.42	3.6	4.05	4.5	4.95	5.4
Tensile Strength CD (ISO 1924-2, kN/m)	1.52	1.6	1.8	2.0	2.2	2.4
Tensile Index MD (Nm/g)	90.0	90.0	90.0	90.0	90.0	90.0
Tensile Index CD (Nm/g)	40.0	40.0	40.0	40.0	40.0	40.0
Tear Strength MD (ISO 1974, mN)	285	300	337.5	375	412.5	450
Tear Strength CD (ISO 1974, mN)	304	320	360	400	440	480
Tear Index MD (Nm ² /kg)	7.5	7.5	7.5	7.5	7.5	7.5
Tear Index CD (Nm ² /kg)	8	8	8	8	8	8
Burst Strength (ISO 2758, kPa)	144.4	152	171	190	209	228
Burst Index (kPam ² /g)	3.8	3.8	3.8	3.8	3.8	3.8

Values are targets only and can be subject to changes over time without prior notice.



ARCTIC PAPER

MUNKEN KRAFT HIGHWHITE from Arctic Paper Munkedal

Munken Kraft HighWhite is a machine finished Bleached Kraft paper with high whiteness, suitable for various bag, wrapping and packaging applications. The paper is produced with a mixture of softwood and hardwood virgin fibre to give it high strength and good printability.

Munken Kraft HighWhite is Cradle to Cradle Certified® at bronze level, has a Cradle to Cradle Products Innovations Institute's Silver Level Material Health Certificate and holds an ISEGA certificate of compliance for food contact. Munken Kraft HighWhite is available with EU Ecolabel, FSC® and PEFC™ certification.



BASIC INFORMATION

Grammages from 70 to 150 g/m²

ENVIRONMENT / SAFETY

ISEGA certificate (food contact), FSC_C020637, PEFC_053399, EU Ecolabel, ISO 14001, EMAS, Paper Profile, Cradle to Cradle Certified®

PRINTING TECHNIQUES

Flexo, Offset

SHADE

Highwhite

SURFACE

Machine Finished

MUNKEN KRAFT HIGHWHITE

Grammage (g/m ²)	70	80	90	100	110	120	130	140	150
Thickness (µm)	91	100	112	125	138	150	163	175	195
Bulk (cm ³ /g)	1.30	1.25	1.25	1.25	1.25	1.25	1.25	1.25	1.30
Roughness (Bendtsen, ml/min)	250	250	250	250	250	250	250	250	350
Opacity (%)	81	85	88	90	91	92	93	94	96
Brightness (ISO 2470/D65, %)	101	101	101	101	101	101	101	101	101
Whiteness (CIE)	141	141	141	141	141	141	141	141	141
Cobb ₆₀ (g/m ²)	25	25	25	25	25	25	25	25	25
Moisture (%)	6	6	6	6	6	6	6	6	6
Tensile Strength MD (ISO 1924-2, kN/m)	6.7	7.5	8.4	9.0	9.5	10.2	10.4	10.5	10.7
Tensile Strength CD (ISO 1924-2, kN/m)	3.2	3.5	3.9	4.0	4.1	4.2	4.3	4.5	4.6
Tensile Index MD (Nm/g)	95	93	93	90	86	85	80	75	71
Tensile Index CD (Nm/g)	45	43	43	40	37	35	33	32	31
Tear Strength MD (ISO 1974, mN)	525	615	720	850	970	1100	1220	1330	1500
Tear Strength CD (ISO 1974, mN)	665	775	900	1000	1200	1380	1530	1680	1870
Tear Index MD (Nm ² /kg)	7.5	7.7	8	8.5	8.8	9.2	9.4	9.5	10
Tear Index CD (Nm ² /kg)	9.5	9.7	10	10	10.9	11.5	11.8	12	12.5
Burst Strength (ISO 2758, kPa)	275	305	330	370	385	395	415	430	445
Burst Index (kPam ² /g)	3.9	3.8	3.7	3.7	3.5	3.3	3.2	3.1	3.0

Values are targets only and can be subject to changes over time without prior notice.