



The following chart  
contemplates the product  
specification sheet.

Check it up and understand the  
Eukaliner® yield advantages.

**Basis Weight (gsm)**

Property	Unit	Tolerance	90	100	110	120	135	150	170	200
<b>Moisture</b>	%	Target	8 ± 1.5							
<b>SCT CD</b>	kN/m	Target	2.53	2.65	2.99	3.11	3.45	3.91	4.72	5.12
		Minimum	2.20	2.30	2.60	2.70	3.00	3.40	4.10	4.45
<b>Bursting Strength</b>	kPa	Target	396	440	484	528	594	660	748	880
		Minimum	360	400	440	480	540	600	680	800
<b>Cobb 120 Top</b>	gH <sub>2</sub> O/m <sup>2</sup>	Maximum	70							
		Target	45							
		Minimum	30							
<b>Cobb 120 Bottom</b>	gH <sub>2</sub> O/m <sup>2</sup>	Maximum	70							
		Target	55							
		Minimum	30							
<b>Porosity Gurley</b>	s/100ml	Maximum	100							
		Target	60							
		Minimum	30							
<b>Ply Bond</b>	J/m <sup>2</sup>	Target	300							
		Minimum	250							
<b>Bendtsen Roughness Top</b>	ml/min	Maximum	900							

Notes: 1- Lab. conditions: 23 ± 1°C and 50 ± 2% R.H. 2- Tolerances based upon 95% confidence limits. 3- Maximum basis weight tolerance: ± 2.5%.



[eukaliner.com.br](http://eukaliner.com.br)



Klabin

[klabin.com.br](http://klabin.com.br)