



eukaliner[®] white

Also discover the yield advantages of **Eukaliner White[®]**

and let our White Top Liner improve the **structure** and **printing quality** of your packaging – as well as the **productivity of your corrugators**.



Basis Weight (gsm)

Property	Unit	Tolerance	125	135	150	175	200
Moisture	%	Target			8 ± 1.5		
SCT CD	kN/m	Target	3.00	3.50	3.90	4.40	5.00
		Minimum	2.80	3.10	3.50	4.00	4.50
Bursting Strength	kPa	Target	500	540	600	700	800
		Minimum	438	473	525	613	700
Cobb 120 Top	gH ₂ O/m ²	Maximum			70		
		Target			45		
		Minimum			30		
Cobb 120 Bottom	gH ₂ O/m ²	Maximum			70		
		Target			55		
		Minimum			30		
Porosity Gurley	s/100ml	Maximum			100		
		Target			70		
		Minimum			30		
Ply Bond	J/m ²	Target			300		
		Minimum			250		
Bendtsen Roughness Top	ml/min	Maximum			650		
Brightness Top	%	Target			80		
		Minimum			75		

Notes: 1- Lab. conditions: 23 ± 1°C and 50 ± 2% R.H. 2- Tolerances based upon 95% confidence limits. 3- Maximum basis weight tolerance: ± 2.5%.

